

FLY BOYA YAPI KİMYASALLARI İNŞ.

SAN. VE TİC. A.Ş.
Anbar Mh. 2973. Sokak No:35/L
Melikgazi/ Kayseri (Serbest Bölge
Karşısı)/ TURKIYE
PHONE: +90 352 501 38 28
Mimarsinan V.D.
VAT No: 3880740581
info@flykimya.com
www.flykimya.com

Creacase C-123

PRODUCT DESCRIPTION

Creacase C-123 is a two-component, highly reactive, flexible hybrid polyurea based spray coating.

USAGE AREAS

- · Roofs
- Terraces
- · Industrial surfaces
- Roads
- · Parking Lots
- Pipes
- Car bedliners
- Pools

GENERAL PROPERTIES

- Fast curing
- Seamless coating application
- · Application on vertical surfaces
- · High mechanical strength
- · Chemical resistance
- Corrosion resistance
- Abrasion resistance
- Environmentally friendly (VOC free)

TECHNICAL PROPERTIES

Polymix: Creacase C-221 **Prepolymer**: Creanate CI-05

	Unit	Prepolymer	Polymix	Method
Density (25°C)	g/cm ³	1.10-1.12	1.00-1.05	ASTM D 4052
Viscosity (25°C)	cР	500-750	300-750	ASTM D 4878
NCO Content	%	15.0-16.0	=	ASTM D 5155
Solid Content	%	100	100	In house test method

The information provided herein is true and accurate to the best of our research, experience and knowledge. However, in the case of changes in the conditions and application methods, nothing in this bulletin is to be taken as a warranty, and previous trials are recommended. For further information and assistance, service is supplied by our technical staff and laboratories.



FLY BOYA YAPI KİMYASALLARI İNŞ. SAN. VE TİC. A.Ş.

Anbar Mh. 2973. Sokak No:35/L Melikgazi/ Kayseri (Serbest Bölge Karşısı)/ TURKIYE PHONE: +90 352 501 38 28 Mimarsinan V.D. VAT No: 3880740581 info@flykimya.com

Creacase C-123

	Unit	Value	Method
Gel Time	sec	8-10	In house test method
Tack Free Time	sec	17-20	In house test method
Hardness	Shore A	85-95	DIN 53505
Tear Strength	N/mm	15-30	ASTM D 624
Elongation	%	400-500	ASTM D 412
Tensile Strength	N/mm ²	10-15	ASTM D 412

APPLICATION METHOD

Creacase C-123 (polymix) and the Creanate CI-05 (prepolymer) should be applied using high pressure and temperature spray equipment in order to ensure homogeneous mixture and application. Prior to the application, surfaces must be free from dust, dirt, oil and similar residues that will prevent the material adhesion.

	Unit	Value
Mixture ratio (iso/poly)	By weight	110/100
	By volume	100/100
Process Temperature	°C	70-80
Process Pressure	bar	120-200

Consumption: For 1 mm thickness polyurea coating 1,1-1,2 kg/m²

STORAGE CONDITIONS / SHELF LIFE / PACKAGING

Storage: Creacase C-123 and Crenate CI-05 is sensitive to moisture and should therefore be stored in sealed packages.

Shelf life: Creacase C-123 Creanate CI-05 can be stored for 6 months in its original sealed packaging at approximately 25°C. Storage at high temperatures shorten the shelf life.

Packaging: Creacase C-123: Available in 200 kg drum Creanate CI-05: Available in 220 kg drum

The information provided herein is true and accurate to the best of our research, experience and knowledge. However, in the case of changes in the conditions and application methods, nothing in this bulletin is to be taken as a warranty, and previous trials are recommended. For further information and assistance, service is supplied by our technical staff and laboratories.



FLY BOYA YAPI KİMYASALLARI İNŞ. SAN VE TİC A S

SAN. VE TİC. A.Ş.
Anbar Mh. 2973. Sokak No:35/L
Melikgazi/ Kayseri (Serbest Bölge
Karşısı)/ TURKIYE
PHONE: +90 352 501 38 28
Mimarsinan V.D.
VAT No: 3880740581
info@flykimya.com
www.flykimya.com

Creacase C-123

NOTICE REGARDING SAFETY AND USAGE

Material Safety Data Sheet (MSDS) will be provided to you by FLY CHEM sales representative during the product supply. It is advisible to review this form before handling and use and also to check your own handling, safety and process contidions. It is necessary to dispose of the finished product drums according to MSDS. FLY CHEM commits protecting human health and the environment during the production conditions and customer conditions. So FLY CHEM is always ready to help its customers in this regard. Please contact to your FLY CHEM representative when you need help.



The information provided herein is true and accurate to the best of our research, experience and knowledge. However, in the case of changes in the conditions and application methods, nothing in this bulletin is to be taken as a warranty, and previous trials are recommended. For further information and assistance, service is supplied by our technical staff and laboratories.